

Technical Information

TI/N-CPN/IP Plastomoll® DNA
May 2023

Page 1 of 3

Supersedes edition dated August 2022

Petrochemicals Plasticizers



Plastomoll® DNA

Plasticizer for PVC products with good low-temperature properties.

Chemical Nature

Diisononyl adipate

BASF Registered Name

Plastomoll® DNA

CAS No.

33703-08-1


Molecular Weight

398

Formula

C₂₄H₄₆O₄

Molecular Structure



Product Specifications

	Value	Test Method
Specific gravity @ 25°/25 °C	0.917 - 0.923	ASTM D-4052
Ester content, % by weight (minimum)	99.6	ASTM D-3465
Acid Number, mg KOH/g (maximum)	0.1	ASTM D-1045
Water, % by weight (maximum)	0.1	ASTM E-203
Color, Pt-Co Units (APHA, maximum)	25	ASTM D-5386
Suspended Matter	COLSFFM*	visual

*Clear Oily Liquid Substantially Free of Foreign Material

Typical Physical Properties

The following data were measured in the BASF Corp. laboratory. They do not represent any legally binding guarantee of properties for our sales product.

	Value
Pour point, °C	-68
Flash point (COC), °C	215
Odor	mild characteristic
Surface Tension, mN/m	30.5
Solution Temperature, °C	154
Plastisol Gelation Temperature, °C	150
Vapor Pressure @ 20 °C, mbar	< 0.01
Solubility @ 25 °C in water, mg/L	< 0.01

Viscosity & Density Data

Temperature (°C)	Dynamic viscosity (cP)	Density (g/cm ³)
-40	1,173	0.968
-30	426	0.960
-20	188	0.952
-10	92.8	0.945
0	51.2	0.937
10	30.9	0.930
20	20.0	0.923
40	9.94	0.908
60	5.80	0.894
80	3.78	0.879

Description

Plastomoll® DNA is a highly efficient plasticizer which imparts excellent low temperature flexibility and resistance to impact to the base resin. For these reasons it finds wide use in polymeric systems based on vinyl, nitrocellulose and rubber. Vinyl plasticized with Plastomoll® DNA has far less volatility than with DOA. It is soluble in the usual organic solvents and is miscible and compatible with all the monomeric plasticizers commonly used in vinyl.

Applications

Plastomoll® DNA can be used in applications requiring an excellent cold flexibility and low volatility.

Safety

Plastomoll® DNA does not require special handling. Handle in accordance with good industrial hygiene and safety practices. Avoid eye contact by wearing personal protective equipment. If eye contact occurs, wash with flowing water and contact physician.

Avoid repeated or prolonged skin contact. Avoid breathing vapors by providing adequate ventilation.

Always refer to the Safety Data Sheet (SDS) for detailed information on safety.

Storage and Handling

Plastomoll® DNA can be stored for one year at temperatures below 40°C, if moisture is excluded.

Packaging

Plastomoll® DNA is available in bulk, tank trucks or rail cars.

Contact Information**Marketing**

BASF Corporation
11750 Katy Freeway, Suite 120
Houston, TX 77079, USA

Tel: +1 800-533-8961
Fax: +1 713-759-3036
E-mail: plasticizers@basf.com

Technical Support

BASF Corporation
4403 La Porte Highway 225
Pasadena, TX, 77501, USA

Tel: +1 281-884-4432
Fax: +1 281-884-4302

Visit us online at

<http://www.plasticizers.basf.com>

Note

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data and information furnished by BASF hereunder are provided gratis and BASF assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

© 2022 BASF Corporation