

## Product Information

CM – Monomers Division

### TECHNICAL DATA SHEET

Document name: TDS\_Lupranat MIPS\_11066112  
Revision: 3 issued: June 26, 2025

Product: **Lupranat® MIPS**  
PBG-No.: 11066112  
Chemical Name: methylene diphenyl diisocyanate

**Chemical nature** Lupranat MIPS is a mixture of 2,4'- and 4,4'-diphenylmethane diisocyanate (MDI). Lupranat MIPS has a lower content of 2,2'- diphenylmethane diisocyanate than Lupranat MI. Lupranat MIPS contains a stabilizer, in order to prevent yellowing.

**Applications** Together with other isocyanates, Lupranat MIPS is used for the manufacture of flexible foams, adhesives, and coatings.

**Typical properties** Appearance: colourless to yellow, clear liquid

|                  |       |                   |
|------------------|-------|-------------------|
| 2,2'-isomer      | ≤ 0.2 | g/100 g           |
| 4,4'-isomer      | 49.5  | g/100 g           |
| Acidity as HCl   | 50    | mg/kg             |
| Density at 25 °C | 1.19  | g/cm <sup>3</sup> |
| Molar mass       | 250   | g/mol             |
| NCO content      | 33.5  | g/100 g           |
| Purity           | 99.5  | g/100g            |

**Delivery** The delivery is by road tankers, in containers containing 1000 l and in non-returnable drums. If delivered in road tankers, temperature during transport should be maintained between 25 °C and 35 °C. If delivered in drums, temperature should not fall below the crystallization point. Exposure to intensive sunlight should be avoided.

**Storage** Lupranat MIPS is sensitive to moisture and may become yellow, particularly on exposure to light and air. The product slowly forms dimeric diphenylmethane diisocyanate, which is seen as a precipitate, and which might influence the properties of the final products if used for special applications. This dimer cannot be removed by heating.

The ideal storage temperature is 25 to 35 °C. Under these conditions and if moisture is excluded, Lupranat MIPS can be stored for at least 3 months. The containers must be kept airtight, storage tanks must be blanketed with dry nitrogen. Prolonged storage at high temperatures can lead to discoloration, an increased dimer content and the product may become turbid.

Storage at temperatures below +16 °C can lead to partial crystallization of 4,4'-MDI. Crystallized product must be melted out immediately by short term heating. The

## Product Information

## CM – Monomers Division

product temperature must not exceed 50 °C. Local overheating must be avoided, because the product will be destroyed at temperatures above 230 °C with consequent gas formation. Rolling of the drums in a hot air oven is the recommended method of dissolving the crystals. After melting out, the contents of the drum must be thoroughly mixed.

More detailed information on transport and storage of isocyanates is given in the ISOPA-Guidelines “For Safe Loading / Unloading Transportation Storage of TDI and MDI in Bulk” and “For the Safe Transportation, Unloading & Storage of Packaged TDI & MDI”.

### **Safety advice and environmental protection**

Labelling, transportation, storage, processing, waste treatment and disposal must comply with national regulations. Occupational exposure limits are to be observed.

Lupranat MIPS is classified as harmful if inhaled. It causes skin irritation and serious eye irritation. It may cause respiratory irritation. It may cause sensitization by inhalation and skin contact. It is suspected of causing cancer. It may cause damage to organs though prolonged or repeated inhalation exposure.

Before processing the product, we recommend reading the safety data sheet.

To avoid accidents, the residual product in the drums must be handled with care. Any water or moisture which is allowed to enter the drum will react with Lupranat MIPS and release carbon dioxide. Unless action is taken to prevent moisture entry or gas entrapment, the drums will become pressurized and could rupture.

If it is intended to use BASF materials for the manufacture of toys or consumer goods (e. g. products which will come into contact with foodstuffs or with the skin) or medical products, national and international regulations have to be observed.

In the case that migration tests or tests of trace monomers are recommended in the special legislations by the manufacturer of consumer goods, the obligation to fulfill these requirements and to conduct tests for the supplied products is still in the hand of the customer. BASF cannot take over this responsibility for the use of its products from our customers.

Where no regulations exist, consumer goods or medical products must at least comply with European legislation. We recommend contacting our Sales and our Ecology and Product Safety departments.

### **Disposal of drums**

Residues of MDI remaining in drums must be decomposed. Please contact our local agencies for further information on national disposal regulations.

### **Note**

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply

## Product Information

## CM – Monomers Division

---

any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.