

Polystyrol 148 H Q

Product description

Polystyrol 148 H Q is a heat resistant, rapid freezing general purpose grade. It is suitable for expanded sheet and film; for blends with high impact polystyrene in heat contact applications; for transparent, impact resistant applications in blends with styrene-butadiene block copolymer resins (SBC).

Processing

Polystyrol 148 H Q can be injection moulded at temperatures between 180 and 260 °C. Recommended mould temperatures are between 10 and 60 °C. Extrusion melt temperature should not exceed 240 °C.

Applications

In blends with high impact polystyrene or SBC: thermoformed articles for packaging of non-food products. As material for physically or chemically foamed sheet. Injection moulded articles for non-food applications.

Physical form and Storage

Avoid direct exposure to sunlight. Polystyrol 148 K Q can be stored in silos.

Product safety

During processing of Polystyrol 148 K Q small quantities of styrene monomer may be released into the atmosphere. At styrene vapour concentrations below 20 ppm no negative effects on health are expected. In our experience, the concentration of styrene does not exceed 1 ppm in well ventilated workplaces – that is where five to eight air changes per hour are made. Further information can be found in our Polystyrol safety data sheets.

Note

The data contained in this publication are based on our knowledge and experience. In any case and in view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

In order to check the availability of products please contact us or our sales agency.

Typical values at 23 °C ¹⁾	Test method	Unit	Values
Mechanical Properties			
Tensile modulus	ISO 527-1/2	MPa	3360
Stress at break	ISO 527-1/-2	MPa	53
Strain at break	ISO 527-1/-2	%	2
Flexural strength	ISO 178	MPa	87
Charpy impact strength	ISO 179/1eU	kJ/m ²	8
Ball indentation hardness at 358 N/30 s	ISO 2039-1	MPa	176
Thermal properties			
Vicat softening temperature VST/B/50	ISO 306	[°C]	99
Vicat softening temperature VST/A/120	ISO 306	[°C]	105
HDT A (1.80 MPa)	ISO 75-1/-2	°C	82
HDT B (0.45 MPa)	ISO 75-1/-2	°C	93
Processing			
Melt volume-flow rate MVR 200 °C/5 kg	ISO 1133	[cm ³ /10 min]	8
Electrical properties			
Volume resistivity	EN 62631-3-1	Ohm * m	>10 ¹⁴
Surface resistivity	EN 62631-3-2	Ohm	>10 ¹⁴
Other properties			
Density	ISO 1183	g/cm ³	1.05

Footnotes

¹⁾ If product name or properties don't state otherwise.