Technical Information

Edition dated May 2020

TBMA



Supersedes edition dated June 2019

tert-Butyl Methacrylate (TBMA)

Methacrylic acid ester, for manufacturing polymers and for use as a feed stock for syntheses

$$\begin{array}{ccc} CH_3 & CH_3 \\ H_2C = \overset{.}{C} - C - O - \overset{.}{C} - CH_3 \\ \overset{.}{O} & \overset{.}{C}H_3 \end{array}$$

CAS No.: 585-07-9 EINECS No.: 209-548-7

Molecular formula

C₈H₁₄O₂

Molar mass: 142.2 kg/kmol

Product specification

Assay (Gas chromatography)
Water content (ASTM E 203)
Acid content (calc. as methacrylic acid)

(ASTM D 1613)

Color on dispatch (APHA, ASTM D 1209) Standard stabilization (HPLC) min. 99.00 % max. 0.050 % max. 0.1000 %

max. 10

200 ± 20 ppm MEHQ

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Other properties

Appearance clear, colorless Physical form liquid Density at 20 °C 0.875 g/cm³ Refractive index nd at 20 °C 1.415 Boiling point 136 °C Freezing point - 48 °C Viscosity at 20 °C 0.97 mPa · s Vapor pressure at 18.5 °C 7.0 mbar

Labelling according to local Directives

see SDS

Technical Information

Edition dated May 2020

TBMA



Applications

tert-Butyl Methacrylate (TBMA) forms homopolymers and copolymers. Copolymers of tert-Butyl Methacrylate (TBMA) can be prepared with acrylic acid and its salts, amides and esters, and with methacrylates, acrylonitrile, maleic acid esters, vinyl acetate, vinyl chloride, vinylidene chloride, styrene, butadiene, unsaturated polyesters and drying oils, etc. tert-Butyl Methacrylate (TBMA) is also a very useful feedstock for chemical syntheses, because it readily undergoes addition reactions with a wide variety of organic and inorganic compounds.

Features & Benefits

tert-Butyl Methacrylate (TBMA) is a monofunctional monomer with a characteristic high reactivity of methacrylates and a bulky hydrophobic moiety. tert-Butyl Methacrylate (TBMA) can be used to impart the following properties to polymers:

- Chemical resistance
- Hydrophobicity
- Hardness
- Scratch resistance
- Adhesion
- Heat resistance
- High solids
- Weatherability

Storage & Handling

In order to prevent polymerization, *tert*-Butyl Methacrylate (TBMA) must always be stored under air, and never under inert gases. The presence of oxygen is required for the stabilizer to function effectively. It has to contain a stabilizer and the storage temperature must not exceed 35 °C. Under these conditions, a storage stability of one year can be expected upon delivery. In order to minimize the likelihood of overstorage, the storage procedure should strictly follow the "first-in-first-out" principle. For extended storage periods over 4 weeks it is advisable to replenish the dissolved oxygen content.

The preferred construction material for tanks and pipes is stainless steel. Carbon steel is also acceptable, although the formation of rust may be a problem with product quality (color). Iron(III)-ions have been shown to be a weak polymerization initiator. If carbon steel is to be used, special procedures should be used to prepare the tank for use. Storage tanks, pumps and pipes should be earthed.

Safety

A Safety Data Sheet has been compiled for *tert*-Butyl Methacrylate (TBMA) that contains up-to-date information on questions relevant to safety.

Technical Information

Edition dated May 2020

TBMA



Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

May 2020