Technical Information

Petrochemicals Specialty Monomers

TI/CP 0014 e September 2016


Page 1 of 2

Supersedes edition dated June 2016

We create chemistry

iso-Tridecyl Methacrylate (C13MA)

Methacrylic acid ester, for manufacturing polymers and for use as a feed stock for syntheses



CAS No.: 85736-97-6 EINECS No.: 288-509-6

Molecular formula

Product specification

 $C_{17}H_{32}O_2$

Assay (Gas chromatography) Water content (ASTM E 203) Acid content (calc. as methacrylic acid) (ASTM D 1613) Color on dispatch (APHA, ASTM D 1209) Standard stabilization (HPLC) Molar mass: 268.4 kg/kmol

min. 99.0 % max. 0.1 % max. 0.05 %

max. 50

100 ± 25 ppm MEHQ

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose. No liability of ours can be derived therefrom.

Other properties

Appearance Physical form Odor Standard stabilization Density at 20 °C Melting point Flash point Vapor pressure at 20 °C clear, colorless to pale yellow liquid characteristics max 20 ppm HQ 0.88 g/cm³ < 0 °C > 100 °C < 0.01 mbar

Labelling according to local Directives

see SDS

Page 2 of 2

Applications	<i>iso</i> -Tridecyl Methacrylate (C13MA) forms homopolymers and copolymers. Copolymers of <i>iso</i> -Tridecyl Methacrylate (C13MA) can be prepared with (meth)acrylic acid and its salts, amides and esters, and with (meth)acrylates, acrylonitrile, maleic acid esters, vinyl acetate, vinyl chloride, vinylidene chloride, styrene, butadiene, unsaturated polyesters and drying oils, etc. <i>iso</i> -Tridecyl Methacrylate (C13MA) is also a very useful feedstock for chemical syntheses, because it readily undergoes addition reactions with a wide variety of organic and inorganic compounds. <i>iso</i> -Tridecyl Methacrylate (C13MA) is a useful monomer in applications such as anaerobic adhesives, vacuum impregnation sealants, high solids acrylic polyols for automotive coatings. If offers a low viscosity and low odor combined with low shrinkage on polymerization.
Features & Benefits	 <i>iso</i>-Tridecyl Methacrylate (C13MA) is a hydrophobic, mono functional Methacrylate monomer with a low glas transition temperature (T₉) and hence is excellent as a flexible and plasticizing monomer. <i>iso</i>-Tridecyl Methacrylate (C13MA) can be used to impart the following properties to polymers: Chemical/water resistance Impact strength Hydrophobicity Low shrinkage Adhesion Weatherability
Storage & Handling	In order to prevent polymerization <i>iso</i> -Tridecyl Methacrylate (C13MA) must always be stored under air, and never under inert gases. The presence of oxygen is required for the stabilizer to function effectively. It has to contain a stabilizer and the storage temperature must not exceed 35 °C. Under these conditions, a storage stability of one year can be expected upon delivery. In order to minimize the likelihood of overstorage, the storage procedure should strictly follow the "first-in-first-out" principle. The preferred construction material for tanks and pipes is stainless steel. Carbon steel is also acceptable, although the formation of rust may be a problem with product quality (color). Iron(III)-ions have been shown to be a weak polymerization initiator. If carbon steel is to be used, special procedures should be used to prepare the tank for use. Storage tanks, pumps and pipes should be earthed.
Safety	A Safety Data Sheet has been compiled for <i>iso</i> -Tridecyl Methacrylate (C13MA) that contains up-to-date information on questions relevant to safety.
Note	The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. September 2016