














# Bio-based<sup>1</sup> Acrylic & Methacrylic Monomers from BASF



Part of our life. Part of your success.

Product Name	Chemical name [Formula]	Polymer Tg [°C]	Bp [°C]	Coatings (Automotive / Industrial)	Emulsions (Coatings / Adhesives)	Adhesives & Sealants	Paper	Leather / Textile	Oilfield	Lubricants	Construction	Rubber / Plastics	Rad / UV Cure	Superabsorbent Polymer (SAP)	Bio-based content <sup>1</sup>
<b>Alkyl Acrylates</b>															
Ethyl Acrylate (EA) [140-88-5]		-24	99,8	x	x	x	x				x	x			40%
2-Octyl Acrylate (2-OA) [42928-85-8]		-47	202	x	x	x	x	x			x	x			73%
Lauryl Acrylate 1214 F (LA 1214 F) [2156-97-0] (C12) [21643-42-5] (C14)	 n = 12, 14	-	296	x	x	x	x	x	x	x			x		81%
Lauryl Acrylate 12 F (LA 12 F) [2156-97-0]	 n = 11	-	296	x	x	x	x	x	x	x			x		80%
Stearyl Acrylate 1618 (SA 1618) [13402-02-3] (C16) [4813-57-4] (C18)	 n = 16, 18	-	160 (3 mbar)	x		x		x	x	x			x		85%
Stearyl Acrylate 18 (SA 18) [4813-57-4]	 n = 18	-	160 (3 mbar)	x		x		x	x	x			x		86%
Behenyl Acrylate 1822 F (BEA 1822 F) [4813-57-4] (C18), [48076-38-6] (C20) [18299-85-9] (C22)	 n = 18, 22	-	410	x		x		x	x	x			x		87%
Behenyl Acrylate 22 F (BEA 22 F) [18299-85-9] (C22)	 n = 21	-	410	x		x		x	x	x			x		88%
<b>Alkyl Methacrylates</b>															
Lauryl Methacrylate 1214 F (LMA 1214 F) [142-90-5] (C12), [2549-53-3] (C14)	 n = 12, 14	-50	308	x	x	x		x	x	x					76%
Cetyl Methacrylate 1618 F (CEMA 1618 F) [2495-27-4] (C16), [32360-05-7] (C18)	 n = 16, 18	-24	190-210 (64 mbar)	x		x		x	x	x					80%
Stearyl Methacrylate 1618 F (SMA 1618 F) [2495-27-4] (C16), [32360-05-7] (C18)	 n = 16, 18	-22	190-210 (64 mbar)	x		x		x	x	x					81%
Stearyl Methacrylate 18 F (SMA 18 F) [32360-05-7]	 n = 17	-	-	x		x		x	x	x					82%
Behenyl Methacrylate 1822 F (BEMA 1822 F) [32360-05-7] (C18), [16669-27-5] (C22)	 n = 18, 22	-	190-210 (64 mbar)	x		x		x	x	x					83%

<sup>1</sup> According to the method ASTM D6866-18 where biogenic carbon is analyzed.

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED GRATIS, IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR ANY RESULTS OBTAINED. ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE OF OUR PRODUCTS, THE READER IS NOT RELIEVED FROM CARRYING OUT ITS OWN INVESTIGATIONS AND MAKING TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. **NEITHER WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NOR ANY GUARANTEES ARE MADE/GRANTED REGARDING PRODUCTS DESCRIBED, OR THEIR PROPERTIES, DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** IN NO CASE SHALL THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION PROVIDED BE CONSIDERED A PART OF ANY SUPPLY AGREEMENT, UNLESS THE PARTIES EXPRESSLY AGREE OTHERWISE.

**Version dated 05/2025**