

Technical Data Sheet**Lupranat® MRSA frozen**

Page: 1 of 4

Version: 02

Edition: 08.19

Chemical nature

Lupranat MRSA frozen is a 4,4'-diphenylmethane diisocyanates (MDI) with high acidity. Lupranat MRSA frozen contains a stabiliser, in order to prevent yellowing.

Applications

Lupranat MRSA frozen is used for the manufacture of prepolymers. It is also used for the production of pigments, adhesives and coatings. Lupranat MRSA frozen must not be used for the production of polyurethane products, which will come into contact with foodstuffs.

Typical properties

Appearance at room

temperature:

white crystalline solid

Appearance as a liquid:

colourless

Molar mass	250	g/mol	
Purity	99.5	g/100 g	titrimetric
NCO-content	33.5	g/100 g	ASTM D 5155-96 A
2,4'-isomer	1.5	g/100 g	GC
Melting point	38.5	°C	ASTM D 1638-74
Acidity as HCl	15	mg/kg	titrimetric
Hydrolysable chlorine	40	mg/kg	titrimetric
Total chlorine	100	mg/kg	ASTM D 1638-74
Viscosity at 42 °C	5	mPa·s	DIN 53 018
Density at 42 °C	1.22	g/cm ³	DIN 51 757
Specific heat at 50 °C	1.5	kJ/(kg · K)	
Latent heat of fusion	110	kJ/kg	

Technical Data Sheet

Page: 2 of 4

Version: 02

Edition 08.19

Lupranat[®] MRSA frozen**Delivery**

Lupranat MRSA frozen can be delivered in following form:

	container	quantity
Lupranat MRSA frozen	non-returnable drum	240 kg

Transport temperature should normally be the same as storage temperature.

Storage

Lupranat MRSA frozen is sensitive to moisture. The products slowly form dimeric diphenylmethanediisocyanate, which is seen as a precipitate and which might influence the properties of the final products if used for special applications. This dimer cannot be removed by heating.

The product should be stored at temperatures below +5 °C, but preferably considerably below 0 °C; under this condition and if moisture and oxygen are excluded, Lupranat MRSA frozen can be stored for at least 6 months.

Drums containing Lupranat MRSA frozen stored at temperatures lower than room temperature must not be opened in a moisture containing atmosphere. Complete warming up to room temperature prior to utilization avoids condensation of moisture on the crystals.

The product can be melted in a hot air oven at an air temperature of 80 °C to 100 °C. The heating period must be as short as possible; during heating the overall temperature of the product must not exceed 70 °C. Local overheating must be avoided, because the product will be destroyed at temperatures above 230 °C with consequent gas production. Rolling of the drums in a hot air oven is the recommended method of dissolving the crystals. After melting out, the contents of the drum must be thoroughly mixed.

More detailed information on transport and storage of isocyanates is given in the ISOPA-Guidelines "For Safe Loading / Unloading Transportation Storage of TDI and MDI in Bulk" and "For the Safe Transportation, Unloading & Storage of Packaged TDI & MDI".

Technical Data Sheet

Page: 3 of 4

Version: 02

Edition 08.19

Lupranat® MRSA frozen**Safety advice and environmental protection**

Labelling, transportation, storage, processing, waste treatment and disposal must comply with national regulations. Occupational exposure limits are to be observed.

Lupranat MRSA frozen is classified as harmful if inhaled. It causes skin irritation and serious eye irritation. It may cause respiratory irritation. It may cause sensitisation by inhalation and skin contact. It is suspected of causing cancer. It may cause damage to organs through prolonged or repeated inhalation exposure.

Before processing the product, we recommend reading the safety data sheet. For further information, consult our Technical Information leaflet "Safety and Precautionary Measures for the Processing of Polyurethane Systems".

In order to avoid accidents, the residual product in the drums must be handled with care. Any water or moisture which is allowed to enter the drum will react with Lupranat MRSA frozen and release carbon dioxide. Unless action is taken to prevent moisture entry or gas entrapment, the drums will become pressurized and could rupture.

If it is intended to use BASF materials for the manufacture of toys or consumer goods (e. g. products which will come into contact with foodstuffs or with the skin) or medical products, national and international regulations have to be observed. Where no regulations exist, consumer goods or medical products must at least comply with European legislation. We recommend contacting our Sales and our Ecology and Product Safety departments.



We create chemistry

Technical Data Sheet

Lupranat[®] MRSA frozen

Page: 4 of 4

Version: 02

Edition 08.19

Disposal of drums

Residues of MDI remaining in drums must be neutralized. Information on disposal is given in our Technical Information „Safety and Precautionary Measures for the Processing of Polyurethane Systems“. Please contact our local agencies for further information on national disposal regulations.

® = registered trademark of BASF

The data contained in this document as well as advice or other support services are based on our current knowledge and experience and are provided according to our best knowledge. In view of many factors that may affect processing and application of our products, this data does not relieve processors from carrying out their own investigations and tests, particularly with regards to the suitability of the goods supplied for the processes and purposes they intend to use them for; neither does this data imply any guarantee of certain properties, or the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, measured values etc. given herein may change without prior notice and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

For further details or questions please contact the BASF entity responsible for your country.
Contact details can be found at www.basf.com/global/en/who-we-are/organization/locations.html.