

## **Lupranol® 1000/1**

Page: 1 of 2  
Version: 04  
Edition: 06.17

### **Chemical nature**

Lupranol 1000/1 is a polypropylene glycol with a molecular weight of 2000.

### **Applications**

Lupranol 1000/1 is used for the production of polyurethane foams and elastomers.

### **Typical properties**

Appearance:	colourless liquid of low viscosity		
OH Number	55	mg KOH/g	DIN 53 240
Viscosity at 25 °C	325	mPa·s	DIN EN 12092
Water Content	≤ 0.05	%	DIN 51 777
Density at 25 °C	1.00	g/cm <sup>3</sup>	DIN 51 757
Colour	≤ 30	Pt/Co, APHA	DIN ISO 6271
Flash Point	> 160	°C	DIN EN 22 719

### **Safety advice**

If it is intended to use BASF Polyurethanes GmbH materials for the manufacture of consumer goods (e. g. products which will come into contact with foodstuffs or drinking water or products which are in contact with the skin, toys) or medical devices, national and international regulations have to be observed.

Where no regulations exist, consumer goods with intended food contact or medical devices must at least comply with European legislation. We recommend contacting our sales department and/or [product-safety-polyurethanes@basf.com](mailto:product-safety-polyurethanes@basf.com).

Especially, in the case that migration tests or tests of trace monomers are recommended in the special legislations by the manufacturer of consumer goods or medical devices, the obligation to fulfill these requirements and to conduct tests on the supplied products is still in the hand of the customer/manufacturer of the final product. BASF Polyurethanes GmbH cannot take over this responsibility for the use of its products from our customers.

## Technical Data Sheet

# Lupranol® 1000/1

Page: 2 of 2

Version: 04

Edition: 06.17

The compliance with legal requirements and generally accepted standards for consumer protection has to be proven for the specific application using the final product

On processing these products, take note of the necessary precautionary measures described in the Material Safety Data Sheets (MSDSs). For further information on safety measures at the processing of polyurethane products consult our Technical Information 'Safety and Precautionary Measures for the Processing of Polyurethane Systems'.

### Supply and storage

Lupranol 1000/1 is supplied in road tankers, in containers containing 1000 l and in non-returnable drums. After supply the product may be stored under appropriate conditions for at least six months. The storage temperature should be as close as possible to the temperature at which the material will be processed. Thermal load due to overheating at heating surfaces higher than 60 °C are to be avoided as a deterioration of the product quality would be caused. Short term warming or cooling of the product to low temperatures does not damage the product. It should however be noted that at low temperatures viscosity increases markedly and this may cause difficulties in processing. Moist and wet conditions are to be avoided.

® = registered trademark of BASF

The data contained in this document as well as advice or other support services are based on our current knowledge and experience and are provided according to our best knowledge. In view of many factors that may affect processing and application of our products, this data does not relieve processors from carrying out their own investigations and tests, particularly with regards to the suitability of the goods supplied for the processes and purposes they intend to use them for; neither does this data imply any guarantee of certain properties, or the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, measured values etc. given herein may change without prior notice and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.