

Lupranol® 2012/1/PX/PVE

Page: 1 of 2

Version: 02

Edition: 06.17

Chemical nature

Polyol-Component: Preparation based on: polyol, additives

Iso-Component: Preparation based on: P-MDI = Lupranat MX 118/1

Applications

Semi finished Polyurethane system for the production of viscoelastic slabstock foams.
The use should be carried out after consultation of the Technical Service of BASF Polyurethanes GmbH.

Typical properties

Characteristics	Unit	Polyol-Comp	Iso-Comp.	Method
Density (25°C)	g/cm ³	1.08	1.20	G 133-08
Viscosity (25°C)	mPa·s	980	30	G 133-07
OH-number	mgKOH/g	53	-	G 133-01
Water content	%	max 0.10	-	G 133-03
NCO content	%	-	32.8	G 133-06

Safety advice

If it is intended to use BASF Polyurethanes GmbH materials for the manufacture of consumer goods (e. g. products which will come into contact with foodstuffs or drinking water or products which are in contact with the skin, toys) or medical devices, national and international regulations have to be observed.

Lupranol® 2012/1/PX/PVE

Page: 2 of 2

Version: 02

Edition: 06.17

Where no regulations exist, consumer goods with intended food contact or medical devices must at least comply with European legislation. We recommend contacting our sales department and/or product-safety-polyurethanes@basf.com.

Especially, in the case that migration tests or tests of trace monomers are recommended in the special legislations by the manufacturer of consumer goods or medical devices, the obligation to fulfill these requirements and to conduct tests on the supplied products is still in the hand of the customer/manufacturer of the final product. BASF Polyurethanes GmbH cannot take over this responsibility for the use of its products from our customers.

The compliance with legal requirements and generally accepted standards for consumer protection has to be proven for the specific application using the final product.

On processing these products, take note of the necessary precautionary measures described in the Material Safety Data Sheets (MSDSs). For further information on safety measures at the processing of polyurethane products consult our Technical Information 'Safety and Precautionary Measures for the Processing of Polyurethane Systems'.

Supply and storage

Lupranol 2012/1/PX/PVE is supplied in road tankers, in containers containing 1000 l and non-returnable drums. After supply the product may be stored under appropriate conditions for at least six months. The storage temperature should be maintained between 20 °C and 30 °C. The storage temperature should be as close as possible to the temperature at which the material will be processed. Moist and wet conditions are to be avoided.

® = registered trademark of BASF

The data contained in this document as well as advice or other support services are based on our current knowledge and experience and are provided according to our best knowledge. In view of many factors that may affect processing and application of our products, this data does not relieve processors from carrying out their own investigations and tests, particularly with regards to the suitability of the goods supplied for the processes and purposes they intend to use them for; neither does this data imply any guarantee of certain properties, or the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights, measured values etc. given herein may change without prior notice and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Polyurethanes GmbH

Elastogranstr. 60
49448 Lemförde,
Germany
Phone: +49 5443 12-0