



















# Acrylic & Methacrylic Monomers from BASF

Part of our life. Part of your success.

Product Name	Chemical name [Formula]	Polymer Tg [°C]	Bp [°C]	Coatings (Automotive / Industrial)	Emulsions (Coatings / Adhesives)	Adhesives & Sealants	Paper	Leather / Textile	Oilfield	Lubricants	Construction	Rubber / Plastics	Rad / UV Cure	Supersorbent Polymer (SAP)	Classic	Low-PCF 1, 2, 3, 4, 5	Zero-PCF 1, 2, 3, 4, 5	Bio-based 6	Cycled <sup>1, 7</sup>	Made with Green Power <sup>8, 9</sup>
<b>Alkyl Acrylates</b>																				
n-Butyl Acrylate (BA) [141-32-2]		-48	148	x	x	x	x	x			x	x		x	x	x		x	x	
2-Ethylhexyl Acrylate (2-EHA) [103-11-7]		-58	216	x	x	x	x	x			x	x		x	x	x		x	x	
Ethyl Acrylate (EA) [140-88-5]		-24	99,8		x	x	x	x			x	x		x	x		x		x	x
Methyl Acrylate (MA) [96-33-3]		-10	80,1		x	x					x	x		x	x	x		x	x	
iso-Butyl Acrylate (IBA) [106-63-8]		-24	138	x	x	x	x	x			x	x		x	x				x	x
tert-Butyl Acrylate (TBA) [1663-39-4]		50	119	x	x	x	x	x			x	x		x	x	x			x	x
2-Octyl Acrylate (2-OA) [42928-85-8]		47	202	x	x	x	x	x			x	x				x		x	x	x
2-Propylheptyl Acrylate (2-PHA) [149021-58-9]		-67	250	x	x	x						x	x	x	x					x
iso-Decyl Acrylate F (IDA F) [1330-61-6]		-58	158 (66 mbar)	x	x	x						x		x	x					x
Heptadecyl Acrylate (C-17A) [1473386-36-5]		-64	-	x		x		x	x		x	x		x	x					x
Lauryl Acrylate 1214 F (LA 1214 F) [2156-97-0] (C12) [21643-42-5] (C14)		-	296	x	x	x	x	x	x	x			x			x		x	x	
Lauryl Acrylate 12 F (LA 12 F) [2156-97-0]		-	296	x	x	x	x	x	x	x			x			x		x	x	
Stearyl Acrylate 1618 (SA 1618) [13402-02-3] (C16) [4813-57-4] (C18)		-	160 (3 mbar)	x		x		x	x	x			x			x		x	x	
Stearyl Acrylate 18 (SA 18) [4813-57-4]		-	160 (3 mbar)	x		x		x	x	x			x			x		x	x	
Behenyl Acrylate 1822 F (BEA 1822 F) [4813-57-4] (C18), [48076-38-6] (C20) [18299-85-9] (C22)		-	410	x		x		x	x	x			x			x		x	x	

Product Name	Chemical name [Formula]	Polymer Tg [°C]	Bp [°C]	Coatings (Automotive / Industrial)	Emulsions (Coatings / Adhesives)	Adhesives & Sealants	Paper	Leather / Textile	Oilfield	Lubricants	Construction	Rubber / Plastics	Rad / UV Cure	Superabsorbent Polymer (SAP)	Classic	Low-PCF 1, 2, 3, 4, 5	Zero-PCF 1, 2, 3, 4, 5	Bio-based 6	Cycled 1, 7	Made with Green Power 8, 9
Behenyl Acrylate 22 F (BEA 22 F) [18299-85-9] (C22)		-	410	x	x			x	x	x			x		x		x			
<b>Acids</b>																				
Glacial Acrylic Acid (GAA) [79-10-7]		105	141	x	x	x					x	x	x	x	x	x				x
Methacrylic Acid (MAA) [79-41-4]		185	162	x	x	x					x	x		x		x				x
<b>Alkyl Methacrylates</b>																				
<i>tert</i> -Butyl Methacrylate (TBMA) [585-07-9]		107	136	x	x	x		x	x			x		x	x	x				x
Cyclohexyl Methacrylate (CHMA) [101-43-9]		105	94 (20 mbar)	x	x	x		x		x	x	x	x	x	x	x				x
2-Ethylhexyl Methacrylate (2-EHMA F) [688-84-6]		-10	228	x	x	x		x		x		x		x	x	x				x
<i>iso</i> -Decyl Methacrylate (IDMA) [29964-84-9]		-30	263	x		x				x				x	x	x				x
Isotridecyl Methacrylate (C13MA) [85736-97-6]		-31	-	x		x				x				x	x	x				x
Lauryl Methacrylate 1214 F (LMA 1214 F) [142-90-5] (C12), [2549-53-3] (C14)		-50	308	x	x	x		x	x	x					x		x			x
Cetyl Methacrylate 1618 F (CEMA 1618 F) [2495-27-4] (C16), [32360-05-7] (C18)		-24	190-210 (64 mbar)	x		x		x	x	x					x		x			x
Stearyl Methacrylate 1618 F (SMA 1618 F) [2495-27-4] (C16), [32360-05-7] (C18)		-22	190-210 (64 mbar)	x		x		x	x	x					x		x			x
Stearyl Methacrylate 18 F (SMA 18 F) [32360-05-7]		-	-	x		x		x	x	x					x		x			x
Behenyl Methacrylate 1822 F (BEMA 1822 F) [32360-05-7] (C18), [16669-27-5] (C22)		-	190-210 (64 mbar)	x		x		x	x	x					x		x			x
<b>PEG Methacrylates</b>																				
Stearyl Polyethyleneglycol Methacrylate 1100 (SPEGMA 1100) [70879-51-5]		-	-			x								x	x					x
Behenyl Polyethyleneglycol Methacrylate 1100 (BEPEGMA 1100) [125441-87-4]		-	-			x								x	x					x
Methyl Polyethyleneglycol Methacrylate 2000 (MPEGMA 2000) [26915-72-0]		-	-			x					x			x	x					x
<b>Hydroxies</b>																				
4-Hydroxybutyl Acrylate (4-HBA) [2478-10-6]		-65	236	x	x	x							x	x	x					x
Hydroxyethylcaprolactone (HECLA) [110489-05-9]		-52	-	x	x	x							x	x	x					x

Product Name	Chemical name [Formula]	Polymer Tg [°C]	Bp [°C]	Coatings (Automotive / Industrial)	Emulsions (Coatings / Adhesives)	Adhesives & Sealants	Paper	Leather / Textile	Oilfield	Lubricants	Construction	Rubber / Plastics	Rad / UV Cure	Superabsorbent Polymer (SAP)	Classic	Low-PCF 1, 2, 3, 4, 5	Zero-PCF 1, 2, 3, 4, 5	Bio-based 6	Cycled 1, 7	Made Using Green Power 8, 9
<b>Functional Monomers</b>																				
Ureido Methacrylate 25% in MMA (UMA 25%) [86261-90-7]		-	101	x	x	x									x					x
Ureido Methacrylate 50% in Water (UMA 50%) [86261-90-7]		-	101	x	x	x									x					x
Dihydrodicyclopentadienyl Acrylate (DCPA) [12542-30-2]		-	81 (0.7 mbar)	x		x						x	x		x					x

<sup>1</sup> According to the mass balance approach details under: [www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/circular-economy/mass-balance-approach/biomass-balance.html](http://www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/circular-economy/mass-balance-approach/biomass-balance.html)

<sup>2</sup> Considering "cradle-to-gate" approach – details under: [www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/quantifying-sustainability/product-carbon-footprint.html](http://www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/quantifying-sustainability/product-carbon-footprint.html)

<sup>3</sup> Learn how BASF calculates products carbon footprint: [www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/quantifying-sustainability/product-carbon-footprint.html](http://www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/quantifying-sustainability/product-carbon-footprint.html)

<sup>4</sup> Considering "biogenic uptake" where plants remove CO2 from the atmosphere through photosynthesis. The raw materials used in BASF's biomass balance approach are plant-based and the biogenic uptake is accounted for in the calculation of the cradle-to-gate product carbon footprint.

<sup>5</sup> Compared to the BASF "classic" version which may vary according to the production site and selected feedstocks (e.g., Bionaphtha or Biomethane).

<sup>6</sup> According to the method ASTM D6866-18 where "biogenic" carbon is analyzed.

<sup>7</sup> Learn how plastic waste and end-of life tires end up in your product: [www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/circular-economy/mass-balance-approach/chemcycling.html](http://www.basf.com/global/en/who-we-are/sustainability/we-drive-sustainable-solutions/circular-economy/mass-balance-approach/chemcycling.html)

<sup>8</sup> Green power is the power generated by renewable sources (e.g., Wind parks, Solar farms), purchased by BASF in compliance with GHG Protocol and allocated to targeted products via mass balance approach.

<sup>9</sup> Learn more about BASF green power initiatives at: [www.basf.com/global/en/who-we-are/organization/group-companies/BASF\\_Renewable-Energy-GmbH.html](http://www.basf.com/global/en/who-we-are/organization/group-companies/BASF_Renewable-Energy-GmbH.html).

WHILE THE DESCRIPTIONS, DESIGNS, DATA AND INFORMATION CONTAINED HEREIN ARE PRESENTED GRATIS, IN GOOD FAITH AND BELIEVED TO BE ACCURATE, THEY ARE PROVIDED FOR GUIDANCE ONLY AND BASF ASSUMES NO OBLIGATION OR LIABILITY FOR ANY RESULTS OBTAINED. ALL SUCH BEING GIVEN AND ACCEPTED AT THE READER'S RISK. BECAUSE MANY FACTORS MAY AFFECT PROCESSING OR APPLICATION/USE OF OUR PRODUCTS, THE READER IS NOT RELIEVED FROM CARRYING OUT ITS OWN INVESTIGATIONS AND MAKING TESTS TO DETERMINE THE SUITABILITY OF A PRODUCT FOR A PARTICULAR PURPOSE PRIOR TO USE. **NEITHER WARRANTIES OF ANY KIND, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NOR ANY GUARANTEES ARE MADE/GRANTED REGARDING PRODUCTS DESCRIBED, OR THEIR PROPERTIES, DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESCRIPTIONS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS.** IN NO CASE SHALL THE DESCRIPTIONS, DESIGNS, DATA OR INFORMATION PROVIDED BE CONSIDERED A PART OF ANY SUPPLY AGREEMENT, UNLESS THE PARTIES EXPRESSLY AGREE OTHERWISE.

**Version dated 06/2024**