

Palatinol® 10-P

Edition dated July 2019

Valid for product produced in Ludwigshafen only

Page 1 of 4

® = Registered trademark of BASF SE

Primary plasticizer for PVC and PVC copolymers

Chemical nature

Phthalic acid ester of isomeric C10 alcohol.

Molecular formula	C ₂₈ H ₄₆ O ₄
CAS number	53306-54-0
EC number	258-469-4
Abbreviation (DIN EN ISO 1043-3)	DPHP

Delivery specification

Property	Value	Unit	Test method DIN/ASTM
Dynamic viscosity* at 20 °C	115 – 130	mPa · s	ASTM D 7042
Density* at 20 °C	0.960 – 0.965	g/cm ³	DIN 51757 ASTM D 4052
Platinum-cobalt color	40 max.		DIN EN ISO 6271 ASTM D 1209
Refractive index* n_D^{20}	1.482 – 1.485		DIN 51423-2 ASTM D 1045
Acid value	0.07 max.	mg KOH/g	DIN EN ISO 2114 ASTM D 1045
Ester content	99.5 min.	% by area	GC-method BASF
Water content	0.05 max.	% by weight	DIN 51777, Part 1 ASTM E 203

*These properties are not measured routinely.

 On request, Palatinol® 10-P can also be supplied in a form stabilized with Irganox® 1010. Please refer to the Technical Information of Palatinol® 10-P Stab (Irganox®).

Properties

Palatino® 10-P is a nearly colorless, clear and practically anhydrous liquid with a hardly noticeable odor. It is soluble in the usual organic solvents and is miscible and compatible with all of the monomeric plasticizers commonly used in PVC. Palatino® 10-P is almost insoluble in water.

Due to its relative low volatility, Palatino® 10-P is most suitable for higher temperature requirement applications, such as wire & cable and automotive interior trim. Because of its good weathering behavior, Palatino® 10-P performs excellent in outdoor applications, such as roofing membranes and tarpaulins.

Physical data

The following physical data were measured in the BASF SE laboratories. They do not represent any legally-binding guarantee of properties for our sales product.

Molar mass	446.7 g/mol
Pour point (DIN ISO 3016)	-48 °C
Solution temperature at the clear point (5 % S-PVC; K-value 71; DIN 53408)	146 °C
Surface tension at 20 °C (DIN EN 14370)	30.4 mN/m
Electrical conductivity 20 °C	0.054 µS/cm
Volume resistivity 20 °C (IEC 60093)	$2 \cdot 10^{12}$ Ohm · cm

Vapor pressure	T [°C]	p [hPa]
	50	$5.7 \cdot 10^{-7}$
	60	$2.5 \cdot 10^{-6}$
	70	$9.4 \cdot 10^{-6}$
	80	$3.2 \cdot 10^{-5}$
	90	$1.0 \cdot 10^{-4}$
	100	$3.0 \cdot 10^{-4}$
	120	$2.0 \cdot 10^{-3}$
	140	$1.1 \cdot 10^{-2}$
	160	$4.6 \cdot 10^{-2}$
	180	0.2
	200	0.5
	220	1.6
	240	4.0
	260	9.4
	280	20.7
	290	29.9
Antoine constants for (p in bar; T in °C)	In (p) = $A + B / (C + T)$	
	A = 13.2599	
	B = -7821.36	
	C = 176.40	

(The Antoine constants were determined from vapor pressure data measured in the temperature range of 200 °C to 290 °C by a dynamic method in a nitrogen atmosphere. The values in the table were calculated using the Antoine equation. The data serve only as a rough guide.)

Density and viscosity dependent on temperature

Temperature [°C]	Density* ρ [g/cm ³]	Dynamic. Viscosity** η [mPa · s]
-10	0.9846	1696
0	0.9772	590
10	0.9698	252
20	0.9624	122
30	0.9550	64
40	0.9476	37
50	0.9403	23

* Calculated using the following equation: $\rho = (-0.000739 \cdot t + 0.97721)$ from data measured by BASF SE. (ρ = Density in g/cm³, t = Temperature in °C)

** Calculated according to Schwen und Puhl ([1], Formula 12) from data measured by BASF SE

Specific heat C_P (DSC) according to DIN 51007

Temperature [°C]	Specific heat C_P [J/(g · K)]
25	1.63
40	1.69
60	1.74
80	1.80
100	1.88

Net and gross calorific value measured according ISO 1716

Net calorific value H_u [MJ/Kg]	Gross calorific value H_o [MJ/Kg]
35.0	37.25

Storage & Handling

Palatinol® 10-P can be stored in tanks and drums constructed from normal carbon steel, e. g. A 283 grade. If severe demands are imposed on the product quality, we recommend to store it in tanks constructed from stainless steel, e. g. AISI TP 316 Ti (German steel No. 1.4541) or aluminum (AlMg3).

It is recommended to take steps to ensure the exclusion of atmospheric moisture, e. g. by storing under a blanket of dry nitrogen, as otherwise the product quality may deteriorate, e. g. the water fraction may rise, or the Palatinol® 10-P may be discolored by rust in normal steel tanks.

Drums containing the product should be kept tightly closed in a well-ventilated place.

Palatinol® 10-P can be stored for one year at temperatures below 40 °C, if moisture is excluded.

Pumps:

Cast-steel centrifugal pumps with a simple slip-ring seal are suitable.

Flange seals:

An example of a suitable material for seals is chemical-resistant Polytetrafluoroethylene (PTFE). Other plastics should be checked for suitability before they are taken into use.

Literature

[1] Schwen, R. und Puhl, H.
“Fehlersuche bei Viskositäet-Temperatur-Messungen”, Erdoel und Kohle-Erdgas-Petrochemie, Vol. 45, April 1992:
Part A: “Problematik, Formelpaket und mathematisches Procedere”, issue 4, pages 161 ff.
Part B: “Resultate, Nuetzlichkeit”, issue 6, pages 253 ff.

Safety

When using this product, the information and advice given in our **Safety Data Sheet** should be observed. Due attention should also be given to the **precautions** necessary for handling chemicals.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

July 2019