


Methyl acrylate

Acrylic ester, for manufacturing polymers and for use as a feedstock for syntheses



CAS No.: 96-33-3
EINECS No.: 202-500-6

Molar mass: 86

Product specification

Assay (Gas chromatography)	min. 99.8 %
Water content (ASTM E 203)	max. 0.05 %
Acid content (calc. as acrylic acid) (ASTM D 1613)	max. 0.009 %
Color on despatch (APHA, ASTM D 1209)	max. 10
Standard stabilization (HPLC BASF or ASTM D 3125)	15 ± 5 ppm MEHQ

The aforementioned data shall constitute the agreed contractual quality of the product at the time of passing of risk. The data are controlled at regular intervals as part of our quality assurance program. Neither these data nor the properties of product specimens shall imply any legally binding guarantee of certain properties or of fitness for a specific purpose and no liability of ours can be derived therefrom.

Other properties

Appearance	Clear, colorless
Physical form	liquid
Odor	penetrating
Refractive index n_D at 20 °C	1.404
Density at 20 °C	0.956 g/cm ³
Boiling point	approx. 80 °C
Freezing point	approx. - 75 °C
Viscosity at 20 °C	0.49 mPa · s
Vapour pressure	
at 0 °C	30.8 mbar
at 20 °C	90.5 mbar
Specific heat of liquid	2.0 kJ/kg °C
Heat of evaporation at boiling point	385.1 kJ/kg
Heat of polymerization	950 kJ/kg
Temperature rating for electrical equipment	T 2 (300–450 °C)

Labelling according to local Directives
see MSDS

Applications

Methyl acrylate forms homopolymers and copolymers. Copolymers of methyl acrylate can be prepared with acrylic acid and its salts, amides and esters, and with methacrylates, acrylonitrile, maleic acid esters, vinyl acetate, vinyl chloride, vinylidene chloride, styrene, butadiene, unsaturated polyesters and drying oils, etc. Methyl acrylate is also a very useful feedstock for chemical syntheses, because it readily undergoes addition reactions with a wide variety of organic and inorganic compounds.

Storage & Handling

In order to prevent polymerization, methyl acrylate must always be stored under air, and never under inert gases. The presence of oxygen is required for the stabilizer to function effectively. It has to contain a stabilizer and the storage temperature must not exceed 35 °C. Under these conditions, a storage stability of one year can be expected. In order to minimize the likelihood of overstorage, the storage procedure should strictly follow the "first-in-first-out" principle. For extended storage periods over 4 weeks it is advisable to replenish the dissolved oxygen content.

Storage tanks and pipes should be made of stainless steel or aluminium. Although methyl acrylate does not corrode carbon steel, there is a risk of contamination if corrosion does occur.

Regulations for the storage of flammable liquids must be observed (explosion-proof electrical equipment, vented tanks with flame arresters etc.). Storage tanks, pumps and pipes must be earthed.

For more detailed information please consult also the brochure "SAFE HANDLING AND STORAGE OF ACRYLIC ESTERS" of EBAM.

Safety

A Material Safety Data Sheet has been compiled for methyl acrylate that contains up-to-date information on all questions relevant to safety.

Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

October 2017